

PRODUCT DATA SHEET

Sika AnchorFix®-2+ Tropical

ANCHORING ADHESIVE FOR MEDIUM TO HIGH LOADS



DESCRIPTION

Solvent and styrene free, epoxy acrylate based, 2-component anchoring adhesive for use in hot and tropical climatic conditions.

USES

Sika AnchorFix®-2+ Tropical may only be used by experienced professionals.

As a fast curing anchoring adhesive for all grades of:

- Rebars / reinforcing steel
- Threaded rods
- Bolts and special fastening systems
- Concrete
- Solid masonry
- Steel

Prior to any application, the suitability of the Sika AnchorFix® Adhesive for the substrate in terms of the desired bond strength, and for the prevention of surface staining or discolouration, must be confirmed by testing in a sample area. This is due to the wide variation of possible substrates, particularly in terms of strength, composition and porosity:

- Hard natural stone
- Solid rock

CHARACTERISTICS / ADVANTAGES

- Fast curing
- Standard guns can be used
- Medium to high load capacity
- ETA Approval available
- Suitable for cracked concrete
- Drinking Water certified
- LEED Attestation available
- Non-sag, even overhead
- Styrene-free
- Low odour
- Low wastage

APPROVALS / CERTIFICATES

- Bonded injection type anchor according to ETAG 001 Part 1 and 5 Option 1, ETA-14/0346, Declaration of Performance 020205010020000011 5034408 (1138), certified by notified product certification body 1020, certificate of constancy of performance 1020-CPR-090-032534, and provided with the CE marking.
- Post installed rebar connection according to ETAG 001 Part 1 and 5 TR 023, ETA-13/0779, Declaration of Performance 020205010020000011 5034408 (1138), certified by notified product certification body 1020, certificate of constancy of performance 1020-CPD-090-036698, and provided with the CE marking
- Drinking Water Certificate: Water Regulations Advisory Scheme Ltd. (WRAS) Approval Number: 1604543

PRODUCT INFORMATION

Packaging	300 mL standard cartridge	12 cartridges per box
		Pallet: 75 boxes
Colour	Component A	Grey
	Component B	Off-white
	Component A + B mixed	Light grey

Shelf life	15 months from date of production All Sika AnchorFix®-2+ Tropical cartridges have the expiry date printed on the label.	
Storage conditions	Stored properly in original, unopened, sealed and undamaged packaging in dry conditions at temperatures between +5 °C and +25 °C. Protect from direct sunlight, heat and moisture.	
Density	~1.60 - 1.75 kg/l (component A) ~1.45 - 1.50 kg/l (component B) ~1.65 - 1.75 kg/l (component A + B mixed)	

TECHNICAL INFORMATION

Compressive Strength	~70 N/mm ² (7 d, +20 °C)	(ASTM D 695)						
Modulus of Elasticity in Compression	~7 000 N/mm ² (7 d, +20 °C)	(ASTM D 695)						
Tensile Strength in Flexure	~29 N/mm ² (7 d, +20 °C)	(ASTM D 790)						
Tensile Strength	~15 N/mm ² (7 d, +20 °C)	(ASTM D 638)						
Modulus of Elasticity in Tension	~3 800 N/mm ² (7 d, +20 °C)	(ASTM D 638)						
Service Temperature	<table border="1"> <tr> <td>Long term</td> <td>-40 °C min. / +50 °C max</td> <td>(ETAG 001, part 5)</td> </tr> <tr> <td>Short term (1 - 2 hours)</td> <td>+80 °C</td> <td></td> </tr> </table>	Long term	-40 °C min. / +50 °C max	(ETAG 001, part 5)	Short term (1 - 2 hours)	+80 °C		
Long term	-40 °C min. / +50 °C max	(ETAG 001, part 5)						
Short term (1 - 2 hours)	+80 °C							

SYSTEMS

System Structure	For design details, please refer to the separate documentation provided: "Technical Documentation Sika AnchorFix®-2+ Tropical" Ref: 870 43 07
-------------------------	---

APPLICATION INFORMATION

Mixing Ratio	Component A : Component B = 10 : 1 by volume		
Layer Thickness	~5 mm max.		
Sag Flow	Non-sag, even overhead		
Product Temperature	Sika AnchorFix®-2+ Tropical must be at a temperature of between +15 °C and +40 °C for application.		
Ambient Air Temperature	+15 °C min. / +40 °C max.		
Dew Point	Beware of condensation. Substrate temperature during application must be at least 3 °C above dew point.		
Substrate Temperature	+15 °C min. / +40 °C max.		
Curing Time	Temperature	Open time - T_{gel}	Curing time - T_{cur}
	+35 °C - +40 °C	3.5 min	40 min
	+30 °C - +35 °C	5 min	50 min
	+25 °C - +30 °C	7.5 min	85 min
	+20 °C - +25 °C	10 min	145 min
	+15 °C - +20 °C*	15 min	5 h

*Minimum cartridge temperature = +15 °C


APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY


Mortar and concrete must be older than 28 days. Substrate strength (concrete, masonry, natural stone) must be verified. Pull-out tests must be carried out if the substrate strength is unknown. The anchor hole must always be clean, dry, free from oil and grease etc. Loose particles must be removed from the holes. Threaded rods and rebars have to be cleaned thoroughly from any oil, grease or any other substances and particles such as dirt etc.

MIXING


Getting the cartridge ready: 300 / 550 / 850 mL




1. Unscrew the cap



2. Cut the film




3. Screw on the static mixer




4. Place the cartridge into the gun and start application


Getting the cartridge ready: 350 mL




1. Unscrew the cap



2. remove the cap



3. screw on the static mixer




4. Place the cartridge into the gun and start application

APPLICATION METHOD / TOOLS

Anchors in solid masonry/concrete:




Drilling of hole with an electric drill to the diameter and depth required. Drill hole diameter must be in accordance with anchor size.



The drill hole must be cleaned with a blow pump or by compressed air, starting from the bottom of the hole. (at least 2x)
Important: use oil-free compressors.




The drill hole must be thoroughly cleaned with the special steel brush (brush at least 2x). The diameter of the brush must be larger than the diameter of the drill hole.




The drill hole must be cleaned with a blow pump or by compressed air, starting from the bottom of the hole. (at least 2x)
Important: use oil-free compressors.




The drill hole must be thoroughly cleaned with the special steel brush (brush at least 2x). The diameter of the brush must be larger than the diameter of the drill hole.




The drill hole must be cleaned with a blow pump or by compressed air, starting from the bottom of the hole. (at least 2x)
Important: use oil-free compressors.




Pump approx. twice until both parts come out uniformly. Do not use this material. Release the gun pressure and clean the cartridge opening with a cloth.



Inject the adhesive into the hole, starting from the bottom, while slowly drawing back the static mixer. In any case avoid entrapping air. For deep holes extension tubing can be used.



Insert the anchor with a rotary motion into the filled drill hole. Some adhesive must come out of the hole.
Important: the anchor must be placed within the open time.



During the resin hardening time the anchor must not be moved or loaded. Wash tools immediately with Sika® Colma Cleaner. Wash hands and skin thoroughly with warm soap water.

FURTHER INFORMATION

For design details, please refer to the separate documentation provided:
Technical Documentation Sika AnchorFix®-2+ Tropical 870 43 05"

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA NORTHERN GULF

Bahrain / Qatar / Kuwait
Tel: +973 177 38188
sika.gulf@bh.sika.com
gcc.sika.com

SIKA SOUTHERN GULF

UAE / Oman / SIC
Tel: +971 4 439 8200
info@ae.sika.com
gcc.sika.com

SIKA SAUDI ARABIA

Riyadh / Jeddah / Dammam
Tel: +966 11 217 6532
info@sa.sika.com
gcc.sika.com



ISO 9001: Sika UAE LLC,
Sika Gulf B.S.C. (c),
Sika Saudi Arabia Co. Ltd,
Sika Qatar LLC
ISO 14001: Sika UAE LLC,
Sika Gulf B.S.C. (c),
Sika Saudi Arabia Co. Ltd
OHSAS: Sika UAE LLC,
Sika Gulf B.S.C. (c)

All products are supplied
under a management
system certified to conform
to the requirements of the
quality, environmental and
occupational health &
safety standards ISO 9001,
ISO 14001 and OHSAS
18001.

SikaAnchorFix-2+Tropical-en-AE-(11-2019)-1-2.pdf

Product Data Sheet

Sika AnchorFix®-2+ Tropical
November 2019, Version 01.02
020205010020000009

