

PRODUCT DATA SHEET

Sikadur[®]-41 CF Slow

3-COMPONENT THIXOTROPIC EPOXY PATCHING MORTAR

DESCRIPTION

Sikadur[®]-41 CF Slow is a thixotropic, 3-component patching and repair mortar, based on a combination of epoxy resins and special fillers, designed for use at higher temperatures between +25 °C and +45 °C. Suitable for use in hot and tropical climatic conditions.

USES

Sikadur[®]-41 CF Slow may only be used by experienced professionals.

As a repair and bonding mortar for:

- Concrete elements
- Hard natural stone
- Ceramics, fiber cement
- Mortar, bricks, masonry
- Steel, iron, aluminium
- Wood
- Polyester, epoxy
- Glass

As a repair mortar:

- Filling of cavities and voids
- Vertical and overhead use
- Corners and edges

As an abrasion and impact resistant wearing course:

- Joint filling and crack sealing
- Joint and crack arris / edge repair

CHARACTERISTICS / ADVANTAGES

Sikadur[®]-41 CF Slow has the following advantages:

- Easy to mix and apply
- Very good adhesion to most construction materials
- High strength mortar
- Thixotropic: non-sag in vertical and overhead applications
- Hardens without shrinkage
- Different coloured components (for mixing control)
- No primer needed
- High initial and ultimate mechanical strength
- Good abrasion resistance
- Good chemical resistance

APPROVALS / CERTIFICATES

Mortar for structural and non-structural repair, tested according to EN 1504-3.

PRODUCT INFORMATION

Composition	Epoxy resin
Packaging	11 kg (A + B + C)
Colour	Component A: grey Component B: black Component C: sand Components A + B + C mixed: concrete grey
Shelf life	24 months from date of production

Storage conditions Store in original, unopened, sealed and undamaged packaging in dry conditions at temperatures between +5 °C and +30 °C. Protect from direct sunlight.

Density ~2.01 kg/l (component A + B + C mixed) (+21 °C)

TECHNICAL INFORMATION

Compressive Strength	Curing time	Curing temperature		(DIN EN 196) (ASTM C 579)
		+35 °C	+45 °C	
	1 d	~67 N/mm ²	~68 N/mm ²	
	3 d	~75 N/mm ²	~77 N/mm ²	
	7 d	~76 N/mm ²	~79 N/mm ²	

Modulus of Elasticity in Compression ~5 000 N/mm² (14 d, +35 °C) (ASTM D 695-95)

Tensile Strength in Flexure	Curing time	Curing temperature		(DIN EN 196)
		+35 °C	+45 °C	
	1 d	~20 N/mm ²	~22 N/mm ²	
	3 d	~25 N/mm ²	~26 N/mm ²	
	7 d	~28 N/mm ²	~28 N/mm ²	

Tensile Strength	Curing time	Curing temperature		(ISO 527)
		+35 °C	+45 °C	
	1 d	~11 N/mm ²	~11 N/mm ²	
	3 d	~12 N/mm ²	~14 N/mm ²	
	7 d	~14 N/mm ²	~16 N/mm ²	

Modulus of Elasticity in Tension ~4 000 N/mm² (14 d, +35 °C) (ISO 527)

Elongation at Break 0.2 ± 0.1 % (7 d, +35 °C) (ISO 527)

Tensile Adhesion Strength	Curing time	Substrate	Curing temperature	Adhesion strength	(EN ISO 4624, EN 1542, EN 12188)
	7 d	Concrete dry	+35 °C	> 4 N/mm ² *	
	7 d	Concrete moist	+25 °C	> 4 N/mm ² *	
	7 d	Steel	+25 °C	11 N/mm ²	
	7 d	Steel	+35 °C	12 N/mm ²	
	7 d	Steel	+50 °C	10 N/mm ²	

*100 % concrete failure

Shrinkage Hardens without shrinkage.

Coefficient of Thermal Expansion 4.8×10^{-5} per °C (Temp. range +23 °C – +60 °C) (EN 1770)

Heat Deflection Temperature	Curing time	Curing temperature	HDT	(ISO 75)
	7 d	+35 °C	+50 °C	

(thickness 10 mm)

APPLICATION INFORMATION

Mixing Ratio Component A : B : C = 2 : 1 : 2.5 by weight.
Component A : B : C = 2 : 1 : 3.4 by volume.

Consumption The consumption of Sikadur®-41 CF Slow is approximately 2.0 kg/m² per mm of thickness.

Layer Thickness 60 millimetre maximum.
When using multiple units, use one after the other. Do not mix the following unit until the previous one has been used in order to avoid a reduction in handling time.

Sag Flow	On vertical surfaces it is non-sag up to 20 millimeter thickness. (EN 1799)		
Product Temperature	Sikadur®-41 CF Slow must be applied at temperatures between +25 °C and +45 °C.		
Ambient Air Temperature	+25 °C min. / +45 °C max.		
Dew Point	Beware of condensation. Substrate temperature during application must be at least 3 °C above dew point.		
Substrate Temperature	+25 °C min. / +45 °C max.		
Substrate Moisture Content	Substrate must be dry or mat damp (no standing water) Brush the adhesive well into the substrate		
Pot Life	Temperature	Potlife*	Open time (EN ISO 9514)
	+25 °C	~120 min	--
	+35 °C	~90 min	--
	+45 °C	~45 min	~45 min
	*200 g The potlife begins when the resin and hardener are mixed. It is shorter at high temperatures and longer at low temperatures. The greater the quantity mixed, the shorter the potlife. To obtain longer workability at high temperatures, the mixed adhesive may be divided into portions. Another method is to chill components A, B and C before mixing them (not below +5 °C).		

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY

Mortar and concrete must be older than 28 days (depends on minimal requirement of strengths). Verify the substrate strength (concrete, masonry, natural stone).
The substrate surface (all types) must be clean, dry or mat damp (no standing water) and free from contaminants such as dirt, oil, grease, existing surface treatments and coatings etc.
Steel substrates must be de-rusted similar to Sa 2.5. The substrate must be sound and all loose particles must be removed.

SUBSTRATE PREPARATION

Concrete, mortar, stone, bricks: substrates must be sound, dry or mat damp (no standing water), clean and free from laitance, ice, grease, oils, old surface treatments or coatings and all loose or friable particles must be removed to achieve a laitance and contaminant free, open textured surface.
Steel: must be cleaned and prepared thoroughly to an acceptable quality that is by blast-cleaning and vacuum. Avoid dew point conditions.

MIXING

Pre-batched units:
Mix components A and B together for at least 3 minutes with a mixing spindle attached to a slow speed electric drill (maximum 300 rpm) until the material becomes smooth in consistency and a uniform grey colour. Then add component C and continue until mixture is homogeneous. Avoid aeration while mixing. Then, pour the whole mix into a clean container and stir again for approximately 1 more minute at low speed to keep air entrapment at a minimum. Mix only that quantity which can be used within its pot life.

APPLICATION METHOD / TOOLS

Brush the adhesive well into the substrate. Sikadur®-31 can be used as primer to improve the bond.
When using a thin layer adhesive, apply the mixed adhesive to the prepared surface with a spatula, trowel, notched trowel, (or with hands protected by gloves).
When applying as a repair mortar use some formwork. When using for bonding metal profiles onto vertical surfaces, support and press uniformly using props for at least 12 hours, depending on the thickness applied (not more than 5 millimetre) and the room temperature. Once hardened check the adhesion by tapping with a hammer.

CLEANING OF EQUIPMENT

Clean all tools and application equipment with Sika® Colma Cleaner immediately after use. Hardened / cured material can only be mechanically removed.

IMPORTANT CONSIDERATIONS

Sikadur® resins are formulated to have low creep under permanent loading. However due to the creep behaviour of all polymer materials under load, the long term structural design load must account for creep. Generally the long term structural design load must be lower than 20 to 25 % of the failure load.

A structural engineer must be consulted for load calculations for the specific application.

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA NORTHERN GULF

Bahrain / Qatar / Kuwait
Tel: +973 177 38188
sika.gulf@bh.sika.com
gcc.sika.com

SIKA SOUTHERN GULF

UAE / Oman / SIC
Tel: +971 4 439 8200
info@ae.sika.com
gcc.sika.com

SIKA SAUDI ARABIA

Riyadh / Jeddah / Damman
Tel: +966 11 217 6532
info@sa.sika.com
gcc.sika.com



ISO 9001: Sika UAE LLC,
Sika Gulf B.S.C. (c),
Sika Saudi Arabia Co. Ltd,
Sika Qatar LLC
ISO 14001: Sika UAE LLC,
Sika Gulf B.S.C. (c),
Sika Saudi Arabia Co. Ltd
OHSAS: Sika UAE LLC,
Sika Gulf B.S.C. (c)

All products are supplied
under a management
system certified to conform
to the requirements of the
quality, environmental and
occupational health &
safety standards ISO 9001,
ISO 14001 and OHSAS
18001.

Product Data Sheet
Sikadur®-41 CF Slow
March 2017, Version 01.01
020204030010000042

Sikadur-41CFSlow-en-AE-(03-2017)-1-1.pdf

