

PRODUCT DATA SHEET

Sikagard®-700 S

SILOXANE BASED WATER REPELLENT IMPREGNATION



DESCRIPTION

Sikagard®-700 S is a one part water repellent impregnation for absorbent cementitious substrates. It penetrates well into the open pores of the substrate, providing durable water repellency, while still allowing water vapour diffusion in both directions.

Sikagard®-700 S complies with the requirements of EN 1504-2 for hydrophobic Impregnation (penetration depth class I).

Suitable for use in hot and tropical climatic conditions.

USES

Sikagard®-700 S is used as water repellent and colourless protective surface treatment on absorbent exposed materials such as concrete, cementitious rendering, concrete tiles, fibre cement, brickwork (clay and lime sand, non-vitrified), natural stone.

Sikagard®-700 S can also be used as hydrophobic primer under solvent based or emulsion protective coating. Sikagard®-700 S is used as water-repellent impregnation (hydrophobic treatment) for absorbent substrates such as concrete in civil engineering or building concrete structures.

- Suitable for protection against ingress (Principle 1, method 1.1 of EN 1504-9)
- Suitable for moisture control (Principle 2, method 2.1 of EN 1504-9)
- Suitable for increasing the resistivity (Principle 8, method 8.1 of EN 1504-9)

CHARACTERISTICS / ADVANTAGES

- Reduction of capillary water absorption
- Reduces efflorescence
- Reduces dirt penetration into the pores
- Improves thermal insulation
- Can be overcoated with solvent based and dispersion coatings
- Higher durability and resistance than conventional silicone based treatments
- Does usually not change the appearance of the substrate
- Does not act as a vapour barrier

SUSTAINABILITY

Sikagard®-700 S is certified according "Low Emitting Materials as per Al Sa'fat - Dubai Green Building Evaluation System" by Dubai Central Laboratory (DCL) certificate No. CL17020432

APPROVALS / CERTIFICATES

- Tested by LPM - qualification test to SIA 162 / 5, Report A-13719-2 dated April 1993 - Water absorption, penetration depth, alkali resistance, water vapour diffusion.
- Follows the requirements of EN 1504-2 for hydrophobic impregnation (class I)

PRODUCT INFORMATION

Composition	Silanes / Siloxanes blend in organic solvent
Packaging	20 L cans and 200 L drums
Appearance / Colour	Colourless liquid
Shelf life	12 months from date of production

Storage conditions	Store in original, unopened, sealed and undamaged packaging in dry condition at temperatures between +5 °C and +30 °C. Protect from moisture and direct sunlight.
Density	~0.800 kg/l (at +20 °C)
Flash Point	Closed cup: ~30 °C (~86 °F)

SYSTEMS

System Structure	1 – 2 coats of Sikagard®-700 S
-------------------------	--------------------------------

APPLICATION INFORMATION

Consumption	~0.300 – 0.500 kg/m ² (0.375 – 0.625 l/m ²) per coat for normally absorbent substrate. In order to ensure durability, a minimum of 2 coats must be applied.
Ambient Air Temperature	+5 °C min. / +30 °C max.
Substrate Temperature	+5 °C min. / +30 °C max.
Substrate Moisture Content	< 5 - 6 % when measured with Tramex method
Waiting Time / Overcoating	Can be overcoated with water/solvent based polymer paints - contact the proposed paint manufacturer for details. When overcoating with Sikagard® or solvent based coating, wait at least 5 hours after the hydrophobic impregnation.
Curing Treatment	Sikagard®-700 S does not require any special curing but must be protected from rain for at least 3 hours at +20 °C.

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY / PRE-TREATMENT

Free of dust, oil, efflorescence and existing paint coatings. Cracks in concrete of more than 200 µm must be repaired prior to application of the hydrophobic treatment. Cleaning is best achieved by brushing with suitable detergents or by light blastcleaning or steam cleaning etc. Best results are obtained on dry, very absorbent substrates. The substrate must look dry with no damp patches.

MIXING

Sikagard®-700 S is supplied ready for use and should not be thinned.

APPLICATION

Sikagard®-700 S is applied by using low pressure spray, brush or roller, working from bottom up taking care not to let the product run. Apply subsequent coats "wet on wet".

CLEANING OF EQUIPMENT

Clean all tools and application equipment with Colma Cleaner immediately after use. Hardened / cured material can only be mechanically removed.

IMPORTANT CONSIDERATIONS

- Minimum age of concrete or mortar: at least 4 weeks.
- Cannot be overcoated with limewash or cement paint.
- If there are strict aesthetic requirements (often when used on natural stone), it is recommended to perform preliminary tests as on some stones a slight darkening of the surfaces may result.
- Sikagard®-700 S is not intended for waterproofing under hydrostatic pressure, in permanent contact with water, or for below ground waterproofing.
- Sikagard®-700 S is not intended to seal visible cracks from moisture ingress.
- Building components not to be coated (example aluminium frames, windows etc.) need to be protected from contact with Sikagard®-700 S. In case of splashes, clean immediately using an additional solvent if necessary.

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA NORTHERN GULF

Bahrain / Qatar / Kuwait
Tel: +973 177 38188
sika.gulf@bh.sika.com
gcc.sika.com

SIKA SOUTHERN GULF

UAE / Oman / SIC
Tel: +971 4 439 8200
info@ae.sika.com
gcc.sika.com

SIKA SAUDI ARABIA

Riyadh / Jeddah / Damman
Tel: +966 11 217 6532
info@sa.sika.com
gcc.sika.com



ISO 9001: Sika UAE LLC,
Sika Gulf B.S.C. (c),
Sika Saudi Arabia Co. Ltd,
Sika Qatar LLC
ISO 14001: Sika UAE LLC,
Sika Gulf B.S.C. (c),
Sika Saudi Arabia Co. Ltd
OHSAS: Sika UAE LLC,
Sika Gulf B.S.C. (c)

All products are supplied
under a management
system certified to conform
to the requirements of the
quality, environmental and
occupational health &
safety standards ISO 9001,
ISO 14001 and OHSAS
18001.

Product Data Sheet

Sikagard®-700 S

June 2019, Version 01.03
020303010010000001

Sikagard-700S-en-AE-(06-2019)-1-3.pdf

