

PRODUCT DATA SHEET

Sikalastic®-152 SA

FIBRE-REINFORCED CEMENTITIOUS MORTAR FOR FLEXIBLE WATERPROOFING AND CONCRETE PROTECTION

DESCRIPTION

Sikalastic®-152 SA is a 2-component, crack-bridging, fibre-reinforced cementitious mortar, with low elastic modulus with special additives for waterproofing and protection of concrete subgrades subject to flexural strain.

Suitable for use in hot and tropical climates.

USES

- Flexible waterproofing and protection of hydraulic structures such as basins, tanks, concrete piping, bridges and canals
- Waterproofing of bathrooms, shower, terraces, balconies, swimming pools before the application of ceramic tiles bonded with adhesives
- Waterproofing and protection of outer walls to be buried into the ground
- Inside waterproofing of light counter pressure water of walls and floors in basements

CHARACTERISTICS / ADVANTAGES

- Flexible waterproofing and concrete protection in one product
- Very good crack-bridging abilities
- Reliable application also in very humid environment
- All components ready delivered, no additional mixing water required
- Applicable also on lightly humid substrate
- Non sagging: easy application also on vertical walls
- Excellent adhesion onto lots of substrates such as concrete, cement mortars, stone, masonry

PRODUCT INFORMATION

Composition	Cement modified with polymers, selected alkali-resistant aggregates, microsilica and fibres.
Packaging	Ready batched 33 kg units: Comp. A (liquid): 8 kg Comp. B (powder): 25 kg
Appearance / Colour	Grey
Shelf life	12 months from the date of production, if stored properly in undamaged original sealed packaging.
Storage conditions	In dry and cool conditions.
Maximum Grain Size	D _{max} : ~0.3 mm

TECHNICAL INFORMATION

Tensile Adhesion Strength	≥ 0.8 N/mm ² (28 d)	(EN 1542)
Crack Bridging Ability	Static ≥ 0.9 mm (+23 °C) Dynamic ≥ 0.2 mm (5 cycles / +23 °C)	(ASTM C 1305)
Water Penetration under Pressure	No penetration at 5 bar water pressure	(DIN 1048-5)

SYSTEMS

System Structure	For bonding tiles or equivalent materials directly on Sikalastic®-152 SA, use SikaCeram® C2 type according to EN 12004 or an adhesive compatible with Sikalastic®-152 SA. The application can take place after the second layer has fully cured.
-------------------------	--

APPLICATION INFORMATION

Mixing Ratio	Comp. A : Comp. B = 8 : 25 (weight)										
Fresh Mortar Density	~1.55 kg/l										
Consumption	This depends on the substrate roughness as a guide: ~1.55 kg/m ² /mm. This figure is theoretical and does not include for any additional material required due to surface porosity, surface profile, variations in level and wastage etc..										
Layer Thickness	Minimum 2 mm with constant thickness, applied in minimum 2 layers (maximum recommended thickness per layer is 2 mm)										
Ambient Air Temperature	+5 °C min. / +40 °C max.										
Substrate Temperature	+5 °C min. / +40 °C max.										
Pot Life	~2 h (+25 °C)										
Waiting Time / Overcoating	Sikalastic®-152 SA must be properly hardened before over coating or contact with water. The following waiting times can be used as a guide: <table><tr><td></td><td>+20 °C</td></tr><tr><td>Waiting time between coats</td><td>~24 hours</td></tr><tr><td>Lining with tiles</td><td>~24 hours</td></tr><tr><td>Coating by emulsion coat</td><td>~2 days</td></tr><tr><td>Immersion in water</td><td>~2 days</td></tr></table> Waiting times may vary depending on humidity of environment and substrate.		+20 °C	Waiting time between coats	~24 hours	Lining with tiles	~24 hours	Coating by emulsion coat	~2 days	Immersion in water	~2 days
	+20 °C										
Waiting time between coats	~24 hours										
Lining with tiles	~24 hours										
Coating by emulsion coat	~2 days										
Immersion in water	~2 days										

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY / PRE-TREATMENT

Substrates must be structurally sound, clean, dry and free of all contaminants such as dirt, oil, grease, cement laitance, coatings and other surface treatments etc.

Clean surfaces by blast cleaning, high-pressure water-jetting (400 bar), wire-brushing, grinding etc., in order to remove all previous coatings, any traces of grease, rust, release agents, cement laitance and any other material which could reduce adhesion. All dust deposits from this preparation must also be removed i.e. by vacuum.

Repair concrete substrates, if necessary, with an appropriate cementitious mortar from the Sika® range of repair materials. The substrate must be adequately

dampened before application. The surface shall not be moist to the touch and shall not be the dark matte (saturated surface dry) appearance.

MIXING

Sikalastic®-152 SA can be mixed with a low speed (~500 r.p.m.) electric drill mixer. Shake carefully Comp. A before using. Then pour ~½ Comp. A into a suitable mixing container and add Comp. B slowly while mixing. When homogeneous, add the remaining amount of Comp. A, and mix thoroughly at least for 3 minutes, until the proper lump-free consistency is reached. Do not add any additional water or other ingredients; each packaging unit must be entirely mixed.

APPLICATION

All connections between the substrate and pipe entries, plant and equipment, light switches etc., must be sealed and watertight. Joints in concrete, pipes, anywhere else in the structure must also be sealed and made watertight.

Use coved details at the floor/wall junctions.

Apply Sikalastic®-152 SA by means of a trowel onto the substrate, exerting a good pressure.

Apply the first coat of Sikalastic®-152 SA using a notched (3 x 3 mm) trowel, with firm even pressure onto the substrate in order to achieve a regular, consistent thickness. As soon as the first layer has hardened, apply the second coat of Sikalastic®-152 SA by trowel, taking care to achieve a uniform and continuous layer, which totally covers the first one.

In highly stressed areas a special alkali-resistant glass fibre fabric (eg. 150 - 160 g/m² and 0.47 mm thick) shall be placed into the first fresh mortar layer. It shall be well trimmed and fully embedded into the mortar avoiding the formation of voids in the coating.

Sikalastic®-152 SA cannot be smoothed using float or sponge trowel. It is possible to smooth the surface as soon as the curing of the product is complete by light abrasion techniques

CLEANING OF EQUIPMENT

Clean all tools and application equipment with water immediately after use. Hardened material can only be mechanically removed.

IMPORTANT CONSIDERATIONS

- Sikalastic®-152 SA shall not be smoothed using a float or sponge trowel
- Protect from rain until at least 24 - 48 hours after application
- Avoid direct contact with chlorinated swimming pool water, Sikalastic®-152 SA needs to be protected by suitable tiling
- Sikalastic®-152 SA is not a vapour barrier, and may transmit vapour tensions to over-applied coatings
- The hardening process is slower when there is a high environmental humidity level, e.g. in closed or inadequately ventilated rooms and basements. Ventilation methods are recommended
- Do not use the product in full sun exposure or in the presence of strong wind, or when it may rain

- When over-coating with solvent paints always carry out preliminary trials to ensure the solvent does not affect the integrity of the waterproofing layer
- Sikalastic®-152 SA is not suitable for vehicular traffic. Pedestrian trafficking is allowed, but only if protected by suitable tiling

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA NORTHERN GULF

Bahrain / Qatar / Kuwait
Tel: +973 177 38188
sika.gulf@bh.sika.com
gcc.sika.com

SIKA SOUTHERN GULF

UAE / Oman / SIC
Tel: +971 4 439 8200
info@ae.sika.com
gcc.sika.com

SIKA SAUDI ARABIA

Riyadh / Jeddah / Damman
Tel: +966 11 217 6532
info@sa.sika.com
gcc.sika.com



ISO 9001: Sika UAE LLC,
Sika Gulf B.S.C. (c),
Sika Saudi Arabia Co. Ltd,
Sika Qatar LLC
ISO 14001: Sika UAE LLC,
Sika Gulf B.S.C. (c),
Sika Saudi Arabia Co. Ltd
OHSAS: Sika UAE LLC,
Sika Gulf B.S.C. (c)

All products are supplied
under a management
system certified to conform
to the requirements of the
quality, environmental and
occupational health &
safety standards ISO 9001,
ISO 14001 and OHSAS
18001.

Product Data Sheet

Sikalastic®-152 SA

January 2018, Version 01.01
020701010020000113

Sikalastic-152SA-en-AE-(01-2018)-1-1.pdf

